

TLE

Project No. \_\_\_\_\_  
Book No. 24

143

Formulations of patches  
with Nelegilire free base

with and without 1.2 Propanediol

(#1) 1430 / <sup>26.0</sup>38 + 1.2 PD / 15 Sel without 1.2 PD

	solids	liq	1/3 liq
GMS 1430 (41% sol)	85.0	207.3	69.1
1.2 PD	<del>26.0</del> 0.0	0.0	0.0
Sel free base	<del>11.3</del> 15.0	15.0	5.0
Et OH	20.0 <i>lv</i>	20.0 <i>lv</i>	10.0 <i>lv</i>

(#2) 1430 / 35 1.2 PD / 15 Sel with 1.2 PD

	solids	liq	1/3 liq
GMS 1430 (41%)	50.0	121.95	40.7
1.2 PD	35.0	35.0	11.7
Sel (free base)	15.0	15.0	5.0
Et OH	20.0	20.0	7.0

26.0  
38.0  
EtOH

Witnessed & Understood by me,

*A. G. ...*

Date

Invent d by

Recorded by

*Libertine*

Date

To Page No. \_\_\_\_\_

Project No. \_\_\_\_\_

Book No. 24

TITLE

Formulation (cont)

TITLE

Pec

From Page No. \_\_\_\_\_

#3

1753 / ~~20~~ 1.2 PD / 15 Sel

without 1.2 PD

	solids	liqu.	1/3 liqu.
Gelva 1753 (28.3%)	85.0	303.6	101.2
1.2 PD	0.0	0.0	0.0
Sol (free base)	15.0	15.0	5.0
EtOH	30.0 <sub>lv</sub>	30.0 <sub>lv</sub>	10.0 <sub>lv</sub>

Sol was mixed with EtOH and added to 1753 while mixing.

#4

1753 / 35 1.2 PD / 15 Sel

	solids	liqu.	1/3 liqu.
Gelva 1753 / 35 1.2 PD / 15 Sel			
Gelva 1753	50.0	171.5 <del>176.75</del>	57.17 <del>58.94</del>
1.2 PD	35.0	35.0	11.7
Sol (free base)	15.0	15.0	5.0
EtOH	20.0	20.0	7.0

EtOH was added to 1753

Sol was mixed with 1.2 PD and added to 1753 while mixing

T Page No. \_\_\_\_\_

Witnessed &amp; Understood by me,

Date

Invented by

Date

Recorded by

Witnessed &amp; U

Liz Coop